

TECHNICAL DATASHEET		
EGGER PRO LAMINATE FLOORING		8/ 31 Classic
Coreboard	E1 HCHO	HDF swell stopp plus
Profile	JUST clic! Patented	The patented EGGER installation system JUST clic! stands for quick and simple installation process without glue. Patented as JUST clic! EP 1 441 087 and EP 1 462 587
Guarantee domestic area	15	according to Egger Guarantee
Guarantee comercial area	5	according to Egger Guarantee
Antistatic properties according EN1815	⚡	yes, < 2 kV
Class of use	31	
European Norm EN13329	EN 13329-31	
Format	CLASSIC	
Dimension mm (length x width)	1292 x 192	
Complete thickness	8	
Thickness of silenizio® special cellulose		
Bevel	-	
	Packaging	
Pallet	One-way-pallet	
Paket information		
	Piece	8
	m2	1,98
	kg	14,46
Pallet information		
	Piece	480
	m2	119,07
	kg	877,00
Classification and general requirements according EN13329		
Abrasion resistance according EN13329, annex E	AC3 (IP ≥ 2000)	
Impact resistance according EN13329, annex H	Big ball: ≥ 500 mm Small ball: ≥ 8 N	
Resistance to staining EN438	Group 1 + 2: level 5 group 3: level 4	
Effect of furniture leg according EN424	No damage shall be visible, when tested with foot Type 0 artefact	
Effect of a castor chair according EN425 (Type W)	No change in appearance or damage	
Thickness swelling according ISO 24336	≤ 18 %	
Tolerance of top layer according EN13329	length ± 0,5 mm width ± 0,1 mm	
Light fastness according EN13329	grey scale ≥ level 4 (EN:20105-A02)	
Static indentation by constant pressure according EN ISO 24343-1	< 0,05	
Surface soundness according EN13329, annex D	≥ 1,0 N/mm ²	
Thermal resistance according to EN 12667	0,07 m ² K/W	



TECHNICAL DATASHEET		
EGGER PRO LAMINATE FLOORING		8/32 Classic WV4 UF
Coreboard	E1 HCHO	HDF swell stopp plus
Profile	UNI fit! Patented	The patented UNI fit! installation system stands for a quick and simple installation process without glue. Produced under the licence of Flooring Industries™.
Guarantee domestic area	20	according to Egger Guarantee
Guarantee commercial area	5	according to Egger Guarantee
Antistatic properties according EN1815		yes, < 2 kV
Class of use	32	
European Norm EN13329	EN 13329-32	
Format	CLASSIC	
Dimension mm (length x width)	1291 x 193	
Complete thickness	8	
Thickness of silenzio® special cellulose		
Bevel	WV4	
Pallet	Packaging One-way-pallet	
Paket information		
	Piece	8
	m2	1,99
	kg	14,46
Pallet information		
	Piece	480
	m2	119,40
	kg	877,00
Classification and general requirements according EN13329		
Abrasion resistance according EN13329, annex E	AC4 (IP ≥ 4000)	
Impact resistance according EN13329, annex H	Big ball: ≥ 750 mm Small ball: ≥ 12 N	
Resistance to staining EN438	Group 1 + 2: level 5 group 3: level 4	
Effect of furniture leg according EN424	No damage shall be visible, when tested with foot Type 0 artefact	
Effect of a castor chair according EN425 (Type W)	No change in appearance or damage	
Thickness swelling according ISO 24336	≤ 18 %	
Tolerance of top layer according EN13329	length ± 0,5 mm width ± 0,1 mm thickness ± 0,5 mm	
Light fastness according EN13329	grey scale ≥ level 4 (EN:20105-A02)	
Static indentation by constant pressure according EN ISO 24343-1	< 0,05	
Surface soundness according EN13329, annex D	≥ 1,25 N/mm2	
Thermal resistance according to EN 12667	0,07 m² K/W	



TECHNICAL DATASHEET		
EGGER PRO LAMINATE FLOORING		8/32 Kingsize
Coreboard		HDF swell stopp plus
Profile		The patented UNI fit! installation system stands for a quick and simple installation process without glue. Produced under the licence of Flooring Industries™.
Guarantee domestic area		according to Egger Guarantee
Guarantee comercial area		according to Egger Guarantee
Antistatic properties according EN1815		yes, < 2 kV
Class of use	32	
European Norm EN13329		
Format	KINGSIZE	
Dimension mm (length x width)	1291 x 327	
Complete thickness	8	
Thickness of silenizio® special cellulose		
Bevel	WV2	-
Pallet	Packaging One-way-pallet	
Paket information		
	Piece	6
	m2	2,53
	kg	18,31
Pallet information		
	Piece	240
	m2	101,20
	kg	755,00
Classification and general requirements according EN13329		
Abrasion resistance according EN13329, annex E	AC4 (IP ≥ 4000)	
Impact resistance according EN13329, annex H	Big ball: ≥ 750 mm Small ball: ≥ 12 N	
Resistance to staining EN438	Group 1 + 2: level 5 group 3: level 4	
Effect of furniture leg according EN424	No damage shall be visible, when tested with foot Type 0 artefact	
Effect of a castor chair according EN425 (Type W)	No change in appearance or damage	
Thickness swelling according ISO 24336	≤ 18 %	
Tolerance of top layer according EN13329	length ± 0,5 mm width ± 0,1 mm thickness ± 0,5 mm	
Light fastness according EN13329	grey scale ≥ level 4 (EN:20105-A02)	
Static indentation by constant pressure according EN ISO 24343-1	< 0,05	
Surface soundness according EN13329, annex D	≥ 1,25 N/mm2	
Thermal resistance according to EN 12667	0,07 m² K/W	



TECHNICAL DATASHEET		
EGGER PRO LAMINATE FLOORING		8/32 Classic
Coreboard	E1 HCHO	HDF swell stopp plus
Profile	JUST clic! Patented	The patented EGGER installation system JUST clic! stands for quick and simple installation process without glue. Patented as JUST clic! EP 1 441 087 and EP 1 462 587
Guarantee domestic area	20 years	according to Egger Guarantee
Guarantee comercial area	5 years	according to Egger Guarantee
Antistatic properties according EN1815	Antistatic	yes, < 2 kV
Class of use		32
European Norm EN13329		EN 13329-32
Format		CLASSIC
Dimension mm (length x width)		1292 x 192
Complete thickness		8
Thickness of silenzio® special cellulose Bevel		-
Pallet		Packaging One-way-pallet
Paket information		
	Piece	8
	m2	1,98
	kg	14,46
Pallet information		
	Piece	480
	m2	119,07
	kg	877,00
Classification and general requirements according EN13329		
Abrasion resistance according EN13329, annex E		AC4 (IP ≥ 4000)
Impact resistance according EN13329, annex H		Big ball: ≥ 750 mm Small ball: ≥ 12 N
Resistance to staining EN438		Group 1 + 2: level 5 group 3: level 4
Effect of furniture leg according EN424		No damage shall be visible, when tested with foot Type 0 artefact
Effect of a castor chair according EN425 (Type W)		No change in appearance or damage
Thickness swelling according ISO 24336		≤ 18 %
Tolerance of top layer according EN13329		length ± 0,5 mm width ± 0,1 mm thickness ± 0,5 mm
Light fastness according EN13329		grey scale ≥ level 4 (EN:20105-A02)
Static indentation by constant pressure according EN ISO 24343-1		< 0,05
Surface soundness according EN13329, annex D		≥ 1,25 N/mm2
Thermal resistance according to EN 12667		0,07 m² K/W

